

PQ 型磁芯
PQ CORES




Fig.1




Fig.2




Fig.3




Fig.4




Fig.5




Fig.6




Fig.7




Fig.8




Fig.9




Fig.10




Fig.11




Fig.12




Fig.13




Fig.14




Fig.15




Fig.16




Fig.17




Fig.18

規格 (Type)	尺寸(Unit : mm)																圖形	磁芯參數				單重 (g/ pcs)	Al-value									
	A	B	C	C1	C2	C3	D	D1	D2	E	E1	E2	F	G	G1	H		J	K	C1 (mm ¹)	Le (mm)		Ae (mm ²)	Ve (mm ³)	GP4	GP4B	GP44	GP47	GP90	GP95	GP95B	GP96
PQ1709	16.9±0.3	4.75±0.1	12.0±0.3				7.15±0.2			14.0±0.3			2.35±0.15	11.3±0.3					Fig.2	0.5	23.1	43.0	995	7.5								
PQ1716SD	17.0±0.4	8.1±0.15	11.0±0.4				7.0±0.2			13.25±0.4			5.15±0.15	9.6±0.15					Fig.2	0.7	34.8	49.4	1719.0	10.8				2400				
PQ20-12.8	20.5+0.3/-0.4	6.4±0.1	14.0±0.4				8.8±0.2			18.0+0.4/-0.35			3.8±0.1	12.2min					Fig.1	0.64	38.6	60.05	2320	12.6	4500	2800	3200	3300	3000	3800	3800	
PQ2014X	20.2±0.5	7.0±0.25	13.8±0.3				8.8±0.15			17.5min			4.35±0.15	12.5min					Fig.1	0.58	33.73	57.6	1942	12.3	3000							
PQ2016.5	20.5±0.4	8.25±0.1	14.0±0.4				8.8±0.2			17.7min			5.3±0.15	12.7min					Fig.1	0.61	38	62	2356	14.4	3200	2900	3300	3400	3100	3700	3700	
PQ2016-1	20.15±0.35	8.3+0.15/-0.1	14.0+0.2/-0.25				8.8+0.1/-0.15			18.15±0.35			5.7+0.15/-0.1	12.7min					Fig.1	0.7	39.17	55.93	2191	13.9	2800	2700	3000	3000	2800	3500	3500	
PQ2016-2	20.6±0.5	8.3±0.2	14.0±0.2				8.8±0.2			18.1min			5.7±0.2	13.5min					Fig.1	0.7	39.17	55.9	2189.6	13.9	2600						3600	
PQ20H	20.5±0.4	6.25±0.2	14.0±0.35				8.8±0.2			18.0±0.4			3.75±0.2	12.0min					Fig.1	0.5	31.4	57.05	1796.8	12								
PQ20A-16.6	20.5±0.4	8.3±0.2	14.0±0.25				8.8±0.2			17.6min			5.3±0.2	13.0min					Fig.1	0.6	38.06	58.24	2330.6	14.1		2600						
PQ2020	20.5±0.5	10.25±0.2	14.0±0.25				8.8±0.15			18.15±0.4			7.3±0.2	12.7min					Fig.1	0.751	45.9	61.1	2803	16.4	2800	2600	2880	3000	2800	3500	3500	
PQ2116	21.0±0.7	8.3±0.15	14.0±0.25				8.8±0.2			17.5min			4.4±0.2	12.3min					Fig.1	0.65	38.38	59.36	2278.1	14.8	3400							
PQ2120	21.0±0.7	10.25±0.25	14.0±0.4				8.8±0.2			17.5min			7.3±0.25	13.3min					Fig.1	0.738	45.4	62	2814.8	17.6	2880							
PQ2216	22.2±0.4	8.3±0.2	14.0±0.4				8.8±0.2			19.2min			5.3±0.2	14.7min					Fig.1	0.73	44.2	60.79	3119	15.3	3000							
PQ2220	22.2±0.4	10.25±0.25	14.0±0.4				8.8±0.2			19.2min			7.3±0.25	14.7min					Fig.1	0.72	47.61	66.18	3150.6	17.6	2500							
PQ2318	23.5±0.5	9.3±0.15	13.1±0.35					18.0min	13.6min	8.9±0.25			6.3±0.15						Fig.3	0.63	43.3	68	2944.4	18.2	3300	3000	3300	3400	3200	3600	3600	3600
PQ2514	26.6+0.4/-0.3	6.9±0.15	16.2±0.3					21.9+0.4/-0.3	16.8+0.4/-0.3	10.4±0.2			4.05±0.15						Fig.3	0.44	38.85	87.6	3403	18.8	4200	4000	4500	4600	4300	5300	5300	
PQ2519B	25.0±0.4	9.45±0.15	17.0±0.3				10.8±0.2			21.8±0.4			6.5±0.2	16.0±0.4					Fig.2	0.517	44.7	86.36	3860.2	24.8	4000	3600	5000	4200	3900	4900	4900	4900
PQ2616	26.5±0.6	8.0±0.125	19.0±0.5				12.0±0.3			22.0min			4.0±0.125	15.5min					Fig.1	0.391	46.3	119	5490	28.2	4800	4800	5400	5500	5100	6500	6500	6500
PQ2616-3	26.5±0.6	8.1±0.15	19.0±0.45				12.0±0.35			22.5±0.6			4.1±0.2	15.6min					Fig.9	0.327	37.9	115.9	4389.7	29						6400		
PQ2618X	25.9+0.3/-0.7	8.8±0.2	19.0±0.3				12.0±0.25			22.1min			6.0±0.2	15.5min					Fig.1			99.6		54.8	6000							
PQ2618J	26.5±0.45	9.0±0.13	19.0±0.45				12.0±0.3			22.5±0.45			6.15±0.15	15.9min					Fig.1	0.428	42.8	100	3052.56	29.2	4700	4300	4800	5000	4500	5700	5700	5700
PQ2620	26.5±0.6	10.1±0.25	19.0±0.5				12.0±0.3			22.0min			6.1±0.25	15.5min					Fig.1	0.397	45.9	115.7	5490	33.4	5500	4700	5500	5400	5000	7000	7000	7000
PQ2620-2	26.5±0.6	10.5±0.15	19.0±0.5				12.0±0.3			22.0min			6.15±0.15	16.0min					Fig.1	0.41	46.9	115.1	5303.1	35				5500				
PQ2621	26.5±0.6	10.5±0.3	19.0±0.5				12.0±0.3			22.0min			6.3±0.3	15.5min					Fig.1	0.397	45.9	115.7	5490	35.6	5100	4700	5800	5400	5000	6300	6300	6300
PQ2625	26.5±0.6	12.8±0.4	19.0±0.45				12.0±0.3			22.0min			8.7±0.3	15.5min					Fig.1	0.472	55.5	118	6530	39.6	4300	4300	4700	4900	4500	6000	6000	6000
PQ2625G	26.7±0.5	12.4±0.2	19.0±0.3				12.0±0.3			22.4min			8.0±0.15	16.8min					Fig.1	0.391	46.3	113	5490	40				4800		6000		
PQ2716	27.2±0.5	8.2±0.2	19.0±0.5				12.0±0.2			23.3min			4.0±0.2	17.0min					Fig.1	0.34	39	114	4443.8	29.2	3000	5150	5700	5800	5400	6800	6800	6800
PQ2717	27.0±0.5	8.4±0.15	19.0±0.45				12.0±0.2			22.7min			3.95±0.15	16.5min					Fig.1	0.328	38.5	117	4502	29.6	6000	5300	5900	6100	5600	7000	7000	7000
PQ2720	27.0±0.6	10.0±0.2	19.0±0.4				12.0±0.2			23.2min			6.0±0.2	16.95min					Fig.1	0.4	45.7	114.5	5233	33.4	5500	4700	5200	5400	4900	6300	6300	6300
PQ2725	27.2±0.5	12.6±0.2	19.0±0.4				12.0±0.2			23.2min			8.6±0.2	16.95min					Fig.1	0.5	56.47	113.5	6381	38.4	4500	4000	5300	4500	4900	6400	6400	6400
PQ2822	28.0±0.6	10.6±0.25	19.0±0.5				12.0±0.3			23.5min			6.6±0.25	17.0min					Fig.1	0.433	49.4	114	5631.6	35				4800				
PQ3019	30.0±0.5	9.5±0.2	20.5±0.4				13.3±0.3			25.05min			6.2±0.2	20.5min					Fig.1	0.395	48.9	123.8	6062.1	37.4	5300	4800	5400	5500	5100	6500	6500	6500
PQ30X-23	30.0±0.5	11.5±0.15	25.2±0.5				20.5±0.4		9.0±0.3	14.4±0.25			7.7±0.2	16.0±0.45					Fig.13	0.368	59.9	162.8	9708.7	51.7							6500	
PQ3113	31.5±0.6	6.6±0.15	20.3±0.3				13.4±0.25			26.8±0.5			3.8±0.2	22.5±0.5					Fig.2	0.349	41.63	119.1	4959.8	29.6	5800							
PQ3217	32.0±0.8	8.1±0.15	22.0±0.5				13.45±0.25			27.5±0.5			4.1±0.15	19.0min					Fig.1	0.48	45.7	154.8	7087.9	39.6	6800	6200	7000	7100	6600	8300	8300	8300
PQ3220	32.2±0.5	10.2±0.3	22.0±0.5				13.4±0.3			27.0min			5.95±0.3	19.5min					Fig.1	0.48	77.12	161	12415.7	46.8	6400	4300	6400	5200	4700	6300	6300	6300
PQ3221	32.5±0.5	10.7±0.2	22.0±0.3				13.4±0.3			27.0min			6.3±0.2	20.0min					Fig.1	0.35	53.99	155.3	8385.6	48.4	3400	5500	6300	6400	5900	7700	7700	7700
PQ3225	32.5±0.8	12.5±0.25	22.0±0.5				13.4±0.3			27.0min			8.4±0.25	19.5min					Fig.1	0.41	65.65	161	10585.9	52.8	5000	5000	5000	5800	5300	7200	7200	7200
PQ3225D	32.5±0.5	12.9±0.2	22.0±0.5				13.4±0.3			27.0min			8.4±0.2	19.5min					Fig.1	0.48	77.12	161	12415.7	54.8	4900	4400	5000	5200	4700	6300	6300	6300
PQ3230	32.5±0.5	15.2±0.3	22.0±0.5				13.4±0.3			27.0min			10.65±0.3	19.5min					Fig.1	0.48	77.12	161	12415.7	60.4	4700	4400	4700	5200	4700	6500	6500	6500
PQ3240X	32.5±0.5	20.0±0.15		23.0±0.4	18.0±0.4		11.0±0.2		15.0±0.25	19.0±0.5			16.0±0.2	22.0±0.5					Fig.11	0.69	96.3	139	13385.7	75.5						4000		
PQ3319	33.2±0.5	9.3±0.15	23.7±0.3	15.0±0.3			29.0±0.5			13.4±0.25			6.5±0.15	19.1REF					Fig.4	0.37	52.63	138.4	7286.1	42.2	5600	5100	5750	5900	4600	7000	7000	7000
PQ3321	33.0±0.5	10.45±0.15	22.0±0.5				13.45±0.25			28.0min			6.15±0.15	21.0min					Fig.1	0.37	51	135	6898	47.4	5900	5100	5700	5800	5400	6900	6900	6900
PQ3325	33.0±0.5	12.5±0.25	22.0±0.5				13.45±0.25			27.7min			8.4±0.25	21.0min					Fig.1	0.37	51	135	6898	53.6	5500	5100	5500	5800	5400	6900	6900	6900
PQ3330	33.0±0.5	15.1±0.2	22.0±0.5				13.4±0.3			27.7min			10.90±0.3	19.0min					Fig.1	0.347	53.99	155.3	8385.6	60.2	4600	5400	4600	4600	5900	7700	7700	7700
PQ3513-1	35.0±0.6	6.80±0.15	18.6±0.35				12.9±0.25			29.8±0.6			4.1±0.15	24.50min					Fig.1	0.421	44.2	105	4641	29.6	4800	4400	4900	5600	5100	5900	5900	5900
PQ3517	35.0±0.6	8																														

PQ3525	35.0±0.6	12.5±0.2	26.0±0.5					14.35±0.25			32.0±0.5			7.60±0.2	23.5min				Fig.1	0.48	88.5	184	16284	62.4	6000	4500	6000	5300	4900	6500	6500	6500
PQ3531	35.0±0.6	15.7±0.2	26.0±0.5					14.35±0.25			32.0±0.5			10.7±0.2	24.0min				Fig.1	0.44	80.61	181.1	14595.1	72.6	4200	4800	4200	5600	5100	6900	6900	6900
PQ3535	35.0±0.6	17.5±0.2	26.0±0.5					14.35±0.25			32.0±0.5			12.50±0.2	23.5min				Fig.1	0.48	88.5	184	16284	78.8	4200	4500	4200	5400	4900	6000	6000	6000
PQ3535A	35.1±0.6	21.0+0/-0.25	26.0±0.5					14.6+0/-0.5			32.0±0.5			15.85+0.5/-0	23.5+2.0/-0				Fig.1	0.566	103.8	183.3	19026.5	89.6	4500	4000	4600	4200	4300	5800	5800	5800
PQ3536-1	35.0±0.6	18.0±0.2	26.0±0.5					13.5±0.25			32.0±0.5			13.0±0.2	23.5min				Fig.1	0.448	87.9	196	17260	80.8	4000	4800	5500	5700	5200	7000	7000	7000
PQ3536-3	35.1+0.9/-0.5	17.875±0.125	26.0+0.8/-0.5					14.35±0.25			31.9min			13.0±0.15	23.50min				Fig.1	0.49	84.7	171.2	14507	82			5300					
PQ3625	36.4±0.4	12.5±0.15	22.6±0.3					14.30±0.25			30.20±0.4			7.5±0.15	28.3±0.4				Fig.7	0.4	46.33	115.7	5365.4	61.8	5100	4600	5500	5400	4900	6300	6300	6300
PQ3628X	36.0±0.5	14.0±0.15		25.0±0.4	18.0±0.4	7.6±0.4		16.0±0.3		12.4±0.25	22.0±0.5			9.5±0.2				Fig.10	0.45	74.4	165.4	12305.76	70.9									5800
PQ3729X	37.0±0.6	14.5±0.15	25.6±0.45					17.0±0.3		15.0±0.25	21.0±0.4			21.0±0.4				Fig.12	0.323	71.3	221	15700	87.3									8700
PQ3811	38.0±0.65	5.7±0.15	21.32±0.4					14.3±0.25			32.80±0.65			2.70±0.15				Fig.2	0.33	41	124.3	5100	31	5900	5400	6000	6200	5700	7000	7000	7000	7000
PQ3813	38.0±0.65	6.4±0.15	21.32±0.4					14.3±0.25			32.30min			3.4±0.15	26.0min			Fig.2	0.386	45.1	116.7	5263	36.2	5300	4800	6000	5500	5100	6400	6400	6400	6400
PQ3813SH	38.0±0.65	6.9+0.2/-0.1	21.32±0.4					14.3±0.25			32.8±0.65			3.4+0.2/-0.1	26.05min			Fig.2	0.333	45.67	137	6258.62	38.6	6100	5500	6200	6400	5900	7000	7000	7000	7000
PQ3814	38.0±0.65	7.3±0.15	21.32±0.4					14.3±0.3			32.8±0.65			4.00±0.25	25.84min			Fig.2	0.36	48.62	134.1	6520	40	5700	5200	5800	6000	5500	7100	7100	7100	7100
PQ38B14	38.0±0.65	6.95±0.15	26.0±0.5					8.4±0.2			34.2±0.65			4.2±0.2	17.0±0.25			Fig.6	0.36	48.36	134.1	6486.3	41	5700	5200	5900	5800	5500	7100	7100	7100	7100
PQ3814A	38.0±0.65	7.2±0.2	21.3±0.4					14.3+0.3/-0.25			32.80±0.65			4.2±0.2	26.0min			Fig.2	0.374	48.6	129.8	6308.6	38.4	5500	5000	5700	6000	5300	6900	6900	6900	6900
PQ3816	38.0±0.65	8.3±0.15	21.32±0.4					14.3±0.25		32.8+0.65/-0.5	26.05min			4.70±0.15	26.05min			Fig.2	0.38	53.66	138	7406	44.4	5500	5000	5600	5800	5300	7500	7500	7500	7500
PQ3819	38.0±0.65	9.4±0.15	21.32±0.4					14.3±0.25		32.8±0.65	25.84min			5.1+0.2/-0.1	25.84min			Fig.2	0.36	58.72	163	9571	49.6	6100	5500	6200	7500	5800	7600	7600	7600	7600
PQ4040	40.5±1.0	20.2±0.2	28.0±0.6					14.9±0.3		37.0±0.6	28.0min			14.9±0.2	28.0min			Fig.1	0.52	104	201	20904	105									6800
PQ4121	40.8±0.7	10.45±0.15	24.0±.45					15.6±0.3		35.6±0.7	27.3min			5.75±0.15	27.3min			Fig.2	0.51	94.13	184.4	17360.8	65.6	4900	4300	5000	6800	4700	6300	6300	6300	6300
PQ41-24.2-1	40.8±0.7	12.1±0.2	24.0±0.45					15.6±0.3		35.6±0.7	27.3min			7.4±0.2	27.3min			Fig.2	0.334	65.8	197	12963	74.2					6200				
PQ4129	41.5±1.0	14.7±0.25	28.0±0.6					14.8±0.3		38.0±0.9	29.0min			9.6±0.25	29.0min			Fig.1	0.39	73.42	184.4	13577	83.2	5900	5200	6000	6100	5600	6900	6900	6900	6900
PQ4140	41.5±1.0	19.9±0.25	28.0±0.6					14.8±0.3		38.0±0.9	29.0min			14.8±0.25	29.0min			Fig.1	0.51	94.13	184.4	17360.8	103.2	3900	4300	4300	5100	4700	5700	5700	5700	5700
PQ4210	41.6±0.60	5.15±0.15	18.0±0.30					14.6±0.3		33.5±0.60	30.40min			2.65±0.2	30.40min			Fig.1	0.396	42.64	107.9	4601.3	30.2	5100	4600	5100	5300	4900	7200	7200	7200	7200
PQ4512	45.0±0.7	6.3±0.15	30.0±0.6					18.0±0.35		39.6±0.7	28.8min			2.8±0.15	28.8min			Fig.1	0.23	47.25	207	9778	59.4									6300
PQ4545	45.0±0.8	22.5±0.3	30.0±0.5					17.0±0.35		39.8min	29.2min			16.5±0.3	29.2min			Fig.1	0.45	116.8	261	30484.8	148.8									6300
PQ4821	47.8±0.7	10.45±0.15	24.0±0.45					17.0±0.3		40.6±0.7	27.3min			5.75±0.15	27.3min			Fig.2	0.305	61.48	202.4	12443.5	78.8	7300	6500	7400	8500	7000	9100	9100	9100	9100
PQ4850	48.0±0.9	25.0±0.15	34.5±0.5	30.5±0.5				25.0±0.3		36.5±0.6	27.2±0.2			17.2±0.2				Fig.14	0.262	118.7	453.8	53865	276									9100
PQ5012	50.0±0.7	6.3±0.15	32.0±0.6					20.0±0.35		44.0±0.7	31.5min			2.8±0.15	31.5min			Fig.1	0.21	45.31	212.1	9611.6	35.6									9100
PQ5012S	50.0±0.7	6.0±0.15	37.0±0.6					20.0±0.35		44.0±0.7	28.45±0.6			2.8±0.2	28.45±0.6			Fig.8	0.12	54.37	272.5	14814.8	89.4									9100
PQ5028A	50.0±0.7	14.0±0.125	32.0±0.6					20.0±0.35	25.5±0.35	44.0±0.7	31.5min			7.0±0.15	31.5min			Fig.1	0.22	70.64	320.2	22616.2	141.6	10200	9150	10500	10800	9800	9100	9100	9100	13000
PQ5032	50.0±0.7	16.0±0.125	32.0±0.6					17.0±0.3		44.0±0.7	31.5min			11.0±0.15	31.5min			Fig.1	0.337	86.76	257.2	22313.3	132.4									9000
PQ5040	50.0±0.7	19.98±0.2	32.0±0.5					20.0±0.35		44.0±0.7	31.5min			13.05±0.2	31.5min			Fig.1	0.22	70.6	320	22592	178	10200	9100	10500	10800	9800	9100	9100	9100	13500
PQ5050	50.0±0.7	25.2±0.2	32.0±0.5					20.0±0.35		44.0±0.7	31.5min			18.3±0.2	31.5min			Fig.1	0.313	105.6	337.4	35649	210	7900	7000	7500	8400	7500	9700	9700	9700	9700
PQ5108	51.2±0.6	4.1±0.15	44.9±0.4					9.0±0.25	32.9±0.4	47.6±0.6	43.6±0.6			1.85±0.15	43.6±0.6			Fig.15	0.338	63.27	187	11931	70.2					7500				
PQ55	55.3+0.9/-0.65	26.9±0.25	34.0±0.6					22.0±0.5		45.3+0.65/-0.3	35.2+0.65/-0.3			19.9±0.25	35.2+0.65/-0.3			Fig.1	0.3	122.3	403.6	49378.5	289									9100
PQ555036-1	55.0±0.8	25.0±0.2	36.0±0.55					22.6±0.35		48.0±0.8	34.9±0.8			18.5±0.25	34.9±0.8			Fig.1	0.3	117.6	391.2	45980.9										9100
PQ5808	58.2±0.6	4.1±0.15	55.9±0.5					10.0±0.3	34.9±0.4	54.6±0.6	48.2±0.6			1.85±0.15	48.2±0.6			Fig.16	0.32	71.15	225.2	16023.3	103									9200
PQ6008	60.2±0.8	4.1±0.15	55.9±0.5					11.0±0.25	33.8±0.4	56.0min	48.6±0.8			1.85±0.15	48.6±0.8			Fig.16	0.3	69.46	235	16324.2	111.7									8500
PQ6057	60.7±0.7	28.7±0.25	39.2±0.6					28.0±0.35		50.8±0.7	35.84±0.7			21.7±0.25	35.84±0.7			Fig.1	0.185	101.8	550.4	56047.6	204.6	13000	11600	13400	13900	12500		9100	9100	17200
PQ6136S	61.0±1.0	18.0±0.2	35.0±0.8					25.0±0.6		53.0±1.0	42.0±1.0			10.0±0.2	42.0±1.0			Fig.1	0.204	91.16	447.8	40823.3	246									12000
PQ6154S	61.0±0.7	27.0±0.2	35.0±0.8					25.0±0.6		53.0±0.7	42.1±1.0			17.0±0.2	42.1±1.0			Fig.1	0.255	121.6	476	57861.2	345.2									10000
PQ6164S	61.0±0.7	32.0±0.2	35.0±0.8					25.0±0.6		53.0±0.7	42.1±1.0			24.0±0.2	42.1±1.0			Fig.1	0.33	146.9	449.1	65962.3	372									10000
PQ6272	62.0±1.0	36.2±0.15	35±0.45					25.0±0.35		54.0±1.0	44.0±1.0			28.2±0.2	44.0±1.0			Fig.1	0.37	163.9	446.7	73214.13	411.4						8500			
PQ6417	56.0±1.0	8.7±0.15	63.9±1.2	52.0±1.0				44.0±0.8		24.0±0.5	19.8min			5.7±0.25	11.0±0.2	31.2±0.4		Fig.17					201									
PQ6417-1	56.0±1.0	8.7±0.15	63.9±1.2	52.0±1.0				44.0±0.8		24.0±0.5	19.8min			5.7±0.25	6.0±0.2	24.0±0.4		Fig.18					197.6									